

Test Report

No. AJFS1901000205FF

Date: JAN.18, 2019

Page 1 of 11

3M CHINA

NO 222, TIANLIN ROAD, SHANGHAI

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: 3M 950**SGS Ref No.:** CZRS20190100016**Style/Item No.:** /**Test Requested:**

EN 45545-2:2013+A1:2015 Railway applications—Fire protection on railway vehicles Part 2: Requirements for fire behaviour of materials and components, and testing according to Table 5 — Material requirement sets (R1)

Test Results: -- See attached sheet --**Test Period:**

Sample Receiving Date : JAN.07, 2019

Test Performing Date : JAN.07, 2019 TO JAN.16, 2019

Signed for and on behalf of
SGS-CSTC Co., Ltd. Anji BranchAllen Zou
Technical ManagerSGS-CSTC Inspection & Testing Services Co., Ltd.
Anji Branch Harbin

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

I. Description of Test specimens

Sample description	Aluminum plate + Glue + Aluminum plate
Color	Silvery
Thickness	About 2.1mm (Substrate + Glue)
Exposed (test) surface	One surface
Size of specimens	T02 ISO 5658-2: About 800mm×155mm
	T03.01 ISO 5660-1: About 100mm×100mm
	T10.01/ T10.02/ T11.01: About 75mm×75mm
Substrate	Aluminum plate, silver, about 1 mm thickness, 2 pieces

II. Summary of test results

III. Requirement set IV. (used for)	Test method reference	Parameter Unit	Test results *
R1 (IN1A; IN1B; IN1D; IN1E; IN4; IN5; IN6A; IN7; IN8; IN9B; IN11; IN12A; IN12B; IN14;F5)	T02 ISO 5658-2	<i>CFE</i> kW/m ²	50
	T03.01 ISO 5660-1: 50 kW/m ²	<i>MARHE</i> kW/m ²	0.1
	T10.01 EN ISO 5659-2: 50 kW/m ²	<i>Ds</i> (4) dimensionless	0.3
	T10.02 EN ISO 5659-2: 50 kW/m ²	<i>VOF₄</i> min	2.6
	T11.01 EN ISO 5659-2: 50 kW/m ²	<i>CIT_G</i> dimensionless	0.006

* For the test details, please see the appendix of this test report.

III. Conclusion

According to the test results, the submitted sample **meets** the requirements of **R1** (detailed in Table 5 of EN 45545-2:2013+A1:2015) for **HL3** Hazard Level Classification.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Criteria for EN 45545-2:2013+A1:2015 Table 5 Material requirement sets (R1)

Requirement set (used for)	Test method reference	Parameter Unit	Requirement Definition	HL1	HL2	HL3
R1 (IN1A; IN1B; IN1D; IN1E; IN4; IN5; IN6A; IN7; IN8; IN9B; IN11; IN12A; IN12B; IN14; F5)	T02 ISO 5658-2	CFE kW/m ²	Minimum	20 _a	20 _a	20 _a
	T03.01 ISO 5660-1: 50 kW/m ²	MARHE kW/m ²	Maximum	a -	90	60
	T10.01 EN ISO 5659-2: 50 kW/m ²	Ds(4) dimensionless	Maximum	600	300	150
	T10.02 EN ISO 5659-2: 50 kW/m ²	VOF ₄ min	Maximum	1200	600	300
	T11.01 EN ISO 5659-2: 50 kW/m ²	CIT _G dimensionless	Maximum	1.2	0.9	0.75

^a If flaming droplets/particles are reported according to 5.3.7 EN 45545-2:2013+A1:2015, during the test ISO 5658-2, or for the special case of materials which do not ignite in ISO 5658-2 and are additionally reported as unclassifiable, the following requirements shall be added:

Test to the requirements of EN ISO 11925-2 with 30s flame application.

The acceptance requirements are:

- flame spread < 150 mm within 60s;
- no burning droplets/particles.

Statements:

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

The test results relate only to the specimens of the product in the form in which were tested.

The specimen was supplied by the sponsor and SGS-CSTC ANJI Branch was not involved in any selection or sampling procedure.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

APPENDIX 1: T02 ISO 5658-2:2006 Lateral flame spread

1. Conditioning

T: 23±2°C, R.H: 50±5%, until the test sample was conditioned to constant mass.

2. Test results

Specimen No.:	1		Heat for Sustained Burning (MJ/m ²)	2		Heat for Sustained Burning (MJ/m ²)	3		Heat for Sustained Burning (MJ/m ²)
	-			-			-		
Time to Ignition: (min:sec)	-			-			-		
Time to Travel	min	sec		min	sec		min	sec	
50 mm	-	-	-	-	-	-	-	-	-
100 mm	-	-	-	-	-	-	-	-	-
150 mm	-	-	-	-	-	-	-	-	-
200 mm	-	-	-	-	-	-	-	-	-
250 mm	-	-	-	-	-	-	-	-	-
300 mm	-	-	-	-	-	-	-	-	-
350 mm	-	-	-	-	-	-	-	-	-
400 mm	-	-	-	-	-	-	-	-	-
450 mm	-	-	-	-	-	-	-	-	-
500 mm	-	-	-	-	-	-	-	-	-
550 mm	-	-	-	-	-	-	-	-	-
600 mm	-	-	-	-	-	-	-	-	-
650 mm	-	-	-	-	-	-	-	-	-
700 mm	-	-	-	-	-	-	-	-	-
750 mm	-	-	-	-	-	-	-	-	-
Duration of Test (min:sec)	10:00			10:00			10:00		
Final Travel (mm)	0			0			0		
CFE (kW/m ²)	50			50			50		

Observations during test: None

Calculated from the data in above table for each specimen for each of the parameters

PARAMETER	SPECIMEN No.			Avg
	1	2	3	
Average Heat for Sustained Burning (Qsb) (MJ/m ²)	-	-	-	-
Critical Heat Flux at Extinguishment (CFE) (kW/m ²)	50	50	50	50

Remark: “-” indicate the test is terminated before 150mm position is reached.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

APPENDIX 2: T03.01 ISO 5660-1:2015 Reaction-to-fire tests — Heat release, smoke production and mass loss rate — Part 1: Heat release rate (cone calorimeter method), Heat flux: 50 kW/m²

1. Conditioning

T: 23 ± 2°C, R.H: 50 ± 5%, until the test sample was conditioned to constant mass.

2. Test result

Sample number	1	2	3	Avg
The exposed surface area of the test specimen/ m ²	0.0088	0.0088	0.0088	0.0088
Irradiance / (kW/m ²)	50	50	50	50
Initial mass / g	53.3	53.3	53.5	53.4
Mass at sustained flaming /g	-	-	-	-
Remained mass / g	52.2	52.6	52.5	52.4
Average rate of specimen mass loss per unit area $\dot{m}_{A,10-90} / (g \cdot m^{-2} \cdot s^{-1})$	0.1	0.1	0.1	0.1
Flashing or transitory flaming time at/s	-	-	-	-
Time to sustained flaming / s	--*	--*	--*	--*
Whether re-insert the spark igniter ¹⁾	No	No	No	---
Maximum heat release rate per unit area/ (kW/m ²)	0.8	1.1	1.5	1.1
Average heat release rate per unit area for 180s after ignition / (kW/m ²) ²⁾	-	-	-	-
Average heat release rate per unit area for 300s after ignition / (kW/m ²)	-	-	-	-
Total heat release / (MJ/m ²)	0.1	0.1	0	0.1
Average effective heat of combustion / (MJ/kg)	0.9	0.7	0	0.5
Total smoke production per unit area over the non-flaming phase /m ² m ⁻²	2.4	3.2	2.8	2.8
Total smoke production per unit area over the flaming phase /m ² m ⁻²	-	-	-	-
Test duration /s ³⁾	1200	1200	1200	1200
Maximum value of average rate of heat emission (MARHE) / kW/m ²	0.3	0	0	0.1
Additional observations ⁴⁾	---			
Special mounting procedures ⁵⁾	Special mounting procedures show in Remark 5)			

Remark: "--*" indicate 20min have elapsed and the specimen has not ignited.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Remark:

- 1) If the flame extinguishes in less than 60 s after turning off the spark, re-insert the spark igniter and turn on the spark within 5 s, do not remove the spark until the entire test is completed.
- 2) The 180 s mean heat release readings shall be compared for the three specimens. If any of these mean readings differ by more than 10 % from the arithmetic mean of the three readings, then a further set of three specimens shall be tested unless the mean value is less than 10 kW m^{-2} .
- 3) Collect all data until:
 - a. 32 min after the time to sustained flaming (the 32 min consist of a 30 min test period, and an additional 2 min post-test period to collect data that will be time-shifted). Data are processed to the time to sustained flaming plus 30 min.
 - b. 30 min have elapsed and the specimen has not ignited;
 - c. XO_2 returns to a value greater than the pre-test value minus $100 \mu\text{l/l}$ of oxygen concentration for 10 min. The end of test is the beginning of the 10 min period
 - d. The mass of the specimen is less than 0.1 g for 60 s. The end of test is the beginning of the 60 s period.
 - e. 20 min (specified in EN 45545-2:2013+A1:2015 T03.01).
- 4) Observe and record physical changes to the sample such as melting, swelling, and cracking.
- 5) Special mounting procedures that were used:
 - a. Samples that intumesce or deform so that they contact the spark plug prior to ignition, or the underside of the cone heater after ignition, shall be tested with the separation of 60 mm between the base plate of the cone heater and the upper surface of the specimen.
 - b. Other dimensionally unstable products, for example products that warp or shrink during testing, shall be restrained against excessive movement. This shall be accomplished with 4 tie wires. A tie wire is then looped around the sample holder and retainer frame assembly, so that it is parallel to and approximately 20 mm away from one of the 4 sides of the assembly. The ends of the wire are twisted together such that the wire is pulled firmly against the retainer frame. Excess wire is trimmed from the twisted section before testing. The 3 remaining wires shall be fitted around the specimen holder and retainer frame assembly in a similar manner, parallel to the three remaining sides.
 - c. Materials that distort so extensively that they cannot be held by 4 wires should be tested using the fine wire grid made of $(0,8 \pm 0,1) \text{ mm}$ with wire spacing of $(20 \pm 2) \text{ mm}$.
 - d. Materials that intumesce in a fluid phase such that molten materials overflow the edge frame or seep between the edge frame and the specimen holder invalidate the test. Therefore, such materials should be tested without the edge frame and should be housed in 0,1 mm thick aluminum tray wrappings which extends 10mm above the top edge of the test specimen.
 - e. Materials, such as fibres, which need to be both physically restrained or compressed to be tested at installed densities should be tested in a wire cage structure made of $(1,0 \pm 0,1) \text{ mm}$ steel wire with $(9 \pm 1) \text{ mm}$ spacing which provides appropriate artificial boundaries to enable the materials to be tested
 - f. No special mounting procedures that were used.
- 6) Heat release rate (per unit area), expressed in kilowatts per square metre curve of specimens is given in figure 1.
- 7) The orifice constant is 0.0511; the exhaust flow rate is $0.024 \pm 0.002 \text{ m}^3/\text{s}$.

To be continued...




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Inspection & Testing Services Co., Ltd.
Anji Branch Harbin

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Curves:



To be continued...



SGS-CSTC Technical Services Co., Ltd.
Anji Branch Harbin

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

APPENDIX 3: T10.01&T10.02 EN ISO 5659-2:2017 Plastics—Smoke generation — Part 2: Determination of optical density by a single- chamber test. Heat flux 50kW/m² without pilot flame, test duration is 10min.

1. Conditioning

T: 23 ± 2 °C, R.H: 50 ± 5%, until the test sample was conditioned to constant mass.

2. Test Results

Parameters	1	2	3	Avg
D _s (1.5)	0.4	0.3	0.5	0.4
D _s (4)	0.2	0.4	0.3	0.3
D _s (10)	1.3	1.5	1.6	1.5
VOF ₄ min	2.5	2.6	2.7	2.6
D _s max	2.2	2.7	3.0	2.6
T (D _s max) s	549	561	557	556

NOTE:

D_s (n) is the specific optical density at nth min;

VOF₄ is the cumulative value of specific optical densities in the first 4 min of the test.

D_s max is the maximum optical density in the test chamber.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

APPENDIX 4: T11.01 EN 45545-2:2013+A1:2015, Annex C Gas analysis in the smoke chamber EN ISO 5659-2, using FTIR technique. Heat flux 50kW/m² without pilot flame, test duration is 10min.

1. Conditioning

T: 23±2°C and R.H 50±5%, until the test sample was conditioned to constant mass.

2. Test results

1) 4 min after the test start

Gas	1	2	3	Avg
Carbon Dioxide (CO ₂)	509.34	470.79	513.75	497.96
Carbon Monoxide (CO)	3.47	3.25	3.36	3.36
Hydrogen Fluoride (HF)	ND	ND	ND	--
Hydrogen Chloride (HCl)	ND	ND	ND	--
Hydrogen Bromide (HBr)	ND	ND	ND	---
Hydrogen Cyanide (HCN)	0.97	0.76	0.86	0.86
Nitrogen Oxides (NO _x)	0.37	0.55	0.74	0.55
Sulphur Dioxide (SO ₂)	ND	ND	ND	---

2) 8 min after the test start

Gas	1	2	3	Avg
Carbon Dioxide (CO ₂)	668.33	680.30	695.97	681.53
Carbon Monoxide (CO)	5.83	6.72	6.83	6.46
Hydrogen Fluoride (HF)	ND	ND	ND	--
Hydrogen Chloride (HCl)	ND	ND	ND	--
Hydrogen Bromide (HBr)	ND	ND	ND	---
Hydrogen Cyanide (HCN)	1.94	2.05	2.27	2.09
Nitrogen Oxides (NO _x)	0.55	0.92	1.29	0.92
Sulphur Dioxide (SO ₂)	ND	ND	ND	---

Where, ND indicates Non-detected.

Note: All values given are in mg/m³.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC (China) Services Co., Ltd.
Anji Branch Harbin

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

3) Calculation of CIT_G

Gas component	Reference concentration; mg/m ³
Carbon Dioxide (CO ₂)	72 000
Carbon Monoxide (CO)	1 380
Hydrogen Fluoride (HF)	25
Hydrogen Chloride (HCl)	75
Hydrogen Bromide (HBr)	99
Hydrogen Cyanide (HCN)	55
Nitrogen Oxides (NO _x)	38
Sulphur Dioxide (SO ₂)	262

$$CIT_G = 0.0805 \cdot \sum_{i=1}^{i=8} \frac{c_i}{C_i}$$

Where,

CIT_G – Conventional Index of Toxicity;

c_i – Concentration of the i^{th} gas;


C_i – Reference concentration of the i^{th} gas.

PARAMETER	1	2	3	Avg
CIT_G (4 min)	0.003	0.002	0.004	0.003
CIT_G (8 min)	0.005	0.006	0.006	0.006

To be continued...



Photo Appendix:



SGS authenticate the photo on original report only

End of Report

